

Technical datasheet

Ti-6Al4V-ELI | ASTM F136

Major specifications

UNS R56401	Titan Grade 23	ISO 5832-3
------------	----------------	------------

Available product forms

Round bars.
The current stock range can be found on www.sd-metals.com.
Further dimensions available upon request.

Key features

Ti-6Al4V-ELI (Extra Low Interstitial) is suitable for use in the biomedical and medical fields as well as for a wide range of industrial applications. In this alloy, the interstitial elements such as oxygen, carbon, and iron are deliberately kept low. Ti 6Al4V-ELI thus exhibits improved fracture toughness and ductility. Ductility (elasticity, formability) improves at low temperatures, which is why Ti-6Al4V-ELI is also used in cryogenic applications (cooling and freezing applications).

Applications

- orthopedic implants
- surgical instruments
- bone screws and plates
- medical devices
- cryogenic applications
- some components used in aviation and aerospace technology

Chemical properties

Composition - limits in %

Al	V	Fe	O	C	Ti
5,50 - 6,50	3,5 - 4,5	max. 0,25	max. 0,13	max. 0,08	Rest

Physical and thermal properties

Density	4,47 g/cm ³
Melting temperature	1649 °C
Beta transus temperature	977 ± 4°C
Thermal conductivity at 20°C	6,6 W/m • °C

Mechanical properties (room temperature)

Yield strength	min. 828 MPa
Tensile strength	min. 895 MPa
Elongation	min. 10 %

All information is subject to change without notice.
The properties correspond to the material in the heading. They may vary for other specifications.
Please contact us for more details.

Team Deutschland und Frankreich

Dirk Verhoeven | +49 211 23 09 99-10 | d.verhoeven@sd-metals.com
Seda Ceyhan | +49 211 23 09 99-20 | s.cejhan@sd-metals.com

Team Export

Thomas Ziert | +49 211 23 09 99-12 | t.ziert@sd-metals.com
Kevin Verhoeven | +49 211 23 09 99-13 | k.verhoeven@sd-metals.com
S+D METALS GmbH | +49 4174 66 94 -0 | www.sd-metals.com